

25502

AIR CONDITIONER FOAM SEAL # 19 & 38

TECHNICAL DATA SHEET

FOAMFLEX # 1710

Property	Specification	Test Method
Composition	Polyether Polyurethane	
Cell Structure	Open	
Density (pcf)	0.90 to 1.00	ASTM D 3574
IFD (lbs/50in ²)	27 to 35	ASTM D 3574
Modulus (ratio of 65% / 25% / ILD)	1.95 min	ASTM D 3574
Tensile Strength (psi)	13 min	ASTM D 3574
Elongation (%)	175 min	ASTM D 3574
Tear Resistance (ppi)	1.8 min	ASTM D 3574
Compression Set (%)	8 max	ASTM D 3574
Resilience	40 min	ASTM D 3574

Rev. 005

03/30/05